1797

PARAMOUNT WIRE CO.

1075 OVINGTON AVE. BROOKLYN, NY 11219

www.parawire.com

phone: (718) 680-0975 fax: (718) 680-4453

MATERIAL SAFETY DATA SHEET

Product Name:

Copper and Copper base alloys in rods, bars, strips, coils, wire, tube, Ingots, cake, cathode, and scrap

Chemical Family: Copper & Copper Alloys

Use of Product;

article fabrication

Product includes the following CDA Alloys:

101	530	330	360	413	505	642	715	757
102	240	332	365	422	508	651	725	762
110	260	335	371	425	509	655	735	770
122	268	340	377	430 .	510	670	740	782
145	270	342	380	434	511	675	741	792
101	272	345	385	462	:519	690	743	
210	280	350	405	454	[:] 521	694	745	
220	314	353	410	482	524	706	752	
226	316	356	411	485	544	710	754	

PHYSICAL DATA

Melting Point: Boiling Point:

1500-2100°F

Specific Gravity: Vapor Pressure: 7.5-9.0 g/cc

The product is a silver or yellow to red solid at room temperature and exhibits no odor. The product is insoluble in water.

CHEMICAL COMPOSITION '

Alloys may contain any or all of the chemical constituents listed below:

 	CAS No.	Range (%)	8 Hr. TWA
 Copper	7440-50-8	45 - 100	1 mg/M3 dust
Zinc Aluminum Icon Lead Manganese Nickel Phosphorus Hilton	7440-66-6 7429-90-5 7439-89-6 7439-92-1 7439-96-5 7440-02-0 7723-14-0 7440-21-3 7440-31-5	0 ~ 43 0 ~ 15 0 ~ 5 0 ~ 5 0 ~ 5 0 ~ 33.0 0 ~ 0.5 0 ~ 4.5 0 ~ 11.0	0.1 mg/M3 Eume 5 mg/M3 oxide 10 mg/M3 10 mg/M3 10 mg/M3 1 mg/M3 1 mg/M3 1 mg/M3 10 mg/M3
Tellerium & Comporda	13494-80-9	0 - 0.5	0.1 mg/M3

FROM : CBC METALS & PARAMOUNT WIRE CO PHONE NO. : 973 674 0727

Mar. 12 2881 11:28AM P2

1. July 2. 1. 15

STOREAGE, FIRE & REACTIVITY

Flash Point: N.A.

Auto-ignition Temp: N.A.

Flammability Limits: N.A.

There are no fire or explosion hazards with these alloys. Never use water as an extinguishing agent around molten metal. Water will react violently with any molten metal.

The alloy is stable, non-hazardous solid at room temperatures. Material may react with acids, bases or oxidizers.

Material does nor present a significant health hazard under normal handling and storeage conditions.

HEALTH HAZARD DATA

under normal handling conditions the solid alloy presents no significant health hazards. Processing of the alloy by dust or fume producing operation (grinding, buffing, forgings, etc.) may result in the potential for exposure to airborn metal particulates or fume. The exposure levels in Section II are relevant to fumes and dusts.

Chronic exposure to copper, sinc, lead and manganese may cause metal fume faver. Symptoms of metal fume faver include favor, fatigue, dryness of throat, head and body ache, favor and chill. Overexposure to copper and lead may result in skin and hair discoloration. Chronic exposure may affect the central neverous system leading to emotional disturbances, gait and balance difficulties and paralysis.

Nickel and lead have been identified as potential cancer causing agents.

The product will not irritate the skin or eyes in bulk form. Particulates may cause dermatitis due to mechanical irritation.

First Aid:

Ingestion: Ingestion of significant amounts of coppers alloy are unlikely. Seek medical help if large quantities of product are ingested.

Inhelation: Remove from exposure to dust or fume if present. Seek medical help if required.

Skin Contact: Wash thoroughly with soap and water.

Eye Contact: Flush with water for at least 15 minutes. Seek modical help if required.

FROM : CBC METALS & PARAMOUNT WIRE CO ! PHONE NO. : 973 674 8727

Mar. 12 2001 11

SPILL PROCEDURES

Product is a non-hazardous solid. No special precautions are required for spills of bulk material. Scrap metal can be reclaimed for rause. Follow Federal, State and local regulations regarding disposal.

SPECIAL PROTECTION INFORMATION

Typically no special protection is required during use of the product beyond that required for the process operation being employed. Where dust or fume levels are greater than those specified in Section II, NIOSH approved respiratory protection should be used.

SPECIAL PRECAUTIONS AND COMMENTS

Wet material should never be charged into a molten bath.

Eye protection should be used when cutting, grinding, machining or buffing product. Eye protection should also be used with any other process that generates dust, fumes or chips.

Wash hands thoroughly after use, especially before eating.

The infomation in this MSDS was obtained from sources which we believe are reliable. However, the information is provided without any representation or warranty, express or implied regarding the accuracy or correctness.

The conditions or methods of handling storage, use and disposal of the product are beyond our control and may be beyond our knowledge. For this and other reasons, we do not assume responsibility and expressly disclaim liabilty for loss, damage, or expense arising out of or in any way connected with the handling, storage, use or disposal of the product.